

bastion



Nitrile Soft Blue Powder Free Gloves



Ultimate solutions in hand protection

Nitrile Soft Blue Powder Free Gloves

Product:	Nitrile Soft Blue Powder Free Gloves
Material:	Nitrile
Type:	Non Sterile
Design:	Ambidextrous
Feature:	Micro Textured Fingers
Cuff:	Beaded
Usage:	Single Use only
Colour:	Ice Blue
Packaging:	100 pcs/inner, 10 inners/carton

Dimensions:

Code	Size	Palm Width (mm)	MGM Length (mm)
BNG7831	XS	70 - 79	Min. 240
BNG7832	S	80 - 89	Min. 240
BNG7833	M	90 - 99	Min. 240
BNG7834	L	100 - 109	Min. 240
BNG7835	XL	110 - 119	Min. 240

Thickness:

Location of Thickness Measurement	Single Wall (mm)
Finger	Min. 0.14
Palm	Min. 0.09
Cuff	Min. 0.05

Physical Properties:

	Before Aging	After Aging
Tensile Strength (MPa)	Min. 14	Min. 14
Elongation (%)	Min. 500	Min. 400

This glove is suitable for use with Chemotherapy drugs as below

Test Chemotherapy Drugs	Minimum Breakthrough Detection Time (Specimen 112/3) (Minutes)
Carmustine (BCNU), 3.3 mg/ml (3,300 ppm)	0.3
Cisplatin, 1.0 mg/ml (1,000 ppm)	>240
Cyclophosphamide (Cytoxan), 20 mg/ml (20,000 ppm)	>240
Dacarbazine (DTIC), 10.0 mg/ml (10,000 ppm)	>240
Doxorubicin Hydrochloride, 2.0 mg/ml (2,000 ppm)	>240
Etoposide (Toposar), 20.0 mg/ml (20,000 ppm)	>240
Fluorouracil, 50.0 mg/ml (50,000 ppm)	>240
Methotrexate, 25 mg/ml (25,000 ppm)	>240
Mitomycin C, 0.5 mg/ml (500 ppm)	>240
Paclitaxel (Taxol), 6.0 mg/ml (6,000 ppm)	>240
Thiotepa, (THT) 10.0 mg/ml (10,000 ppm)	16.0
Vincristine, 1.0mg/ml (1,000 ppm)	>240
Fentanyl Citrate Injection, 100mcg/2ml	>240
Ifosfamide, 50.0 mg/ml (50,000 ppm)	>240

Test results provided in accordance with ASTM D 6978 by Akron Rubber Development Laboratory Inc. – Akron, Ohio 44305



ARTG 174353



ASTM D6319

EN374
EN455